


All around you.

EFDC-7050

LLDPE Film Extrusion Resin



DESCRIPTION

EFDC-7050 is a linear low-density polyethylene (LLDPE) resin for tubular blown film extrusion. Films extruded from EFDC-7050 have good toughness and high tensile strength and puncture resistance. The product offers excellent draw down capability for making thinner gauge films. EFDC-7050 contains high levels of slip and antiblocking agent.

APPLICATIONS

EFDC-7050 is recommended for the manufacture of thin gauge liner films, garment bags and films for other industrial, food packaging and other general-purpose applications requiring toughness and puncture resistance.



All around you.

TYPICAL PROPERTIES

Properties	Units	Test Method	Typical Value	
Resin Properties				
Melt Index, I ₂ 16	g/10 min	ASTM D 1238	2.0	
Density	g/cm ³	ASTM D 1505	0.918	
Melting Point	°C	EQUATE	124	
Blown Film Properties*				
Tensile Strength@ Break	MD	MPa	ASTM D 882	31
	TD			23
Elongation @ Break	MD	MPa	ASTM D 882	800
	TD			850
1% Secant Modulus	MD	MPa	ASTM D 882	195
	TD			220
Elmendorf Tear	MD	N/mm	ASTM D 1922	31
	TD			124
Dart Impact, F ₅₀	g	ASTM D 1709 A	85	
Puncture Energy	J/mm	EQUATE	50	
Haze	%	ASTM D 1003	14	
Gloss, 45°	-	ASTM D 2457	50	

* Film properties are typical of 25 micron blown film extruded at 2:1 blow-up ratio.

ASTM: American Society for Testing and Materials

Values shown are typical and not to be construed as specification.

TYPICAL EXTRUSION CONDITIONS

Extrusion Temperatures, °C	180-210
Adapter, Head and Die, °C	210
Melt Temperature, °C	210
Die gap, mm	> 1.8

FOOD CONTACT USAGE

Food contact suitability certificates are available upon request.

AVAILABILITY

EFDC-7050 is supplied in 25-Kg bags in secured pallets of 55 bags (1.375 MT net) and in sea bulk containers.

STORAGE AND HANDLING

EFDC-7050 is supplied in pellet form and is readily conveyed on conventional polyethylene bulk handling equipment. The bulk handling system should be designed to prevent accumulation of fines and dust particles that can pose an explosion hazard. Ensure all equipment is properly grounded. The product should be stored in a cool dry shaded area away from dust, sunlight and heat. Also carefully review the **Material Safety Data Sheet (MSDS)** supplied with this product for health, safety and waste considerations.

IMPORTANT NOTICES

- IV. The information supplied in this bulletin to the best of our knowledge is accurate and factual as of the date printed. It is offered solely as a convenience to EQUATE's customers and is intended only as a guide for EFDC-7050. Since the user's specific applications and conditions of use are beyond EQUATE's control, EQUATE makes no warranty or representation regarding results that may be obtained by the user. It shall be the responsibility of the user to determine the suitability of the product for the user's specific application. The information disclosed in this document is not to be construed as a recommendation to use the product in infringement of any patent rights covering the usage.
- V. Regarding medical application restrictions EQUATE Petrochemical Company does not recommend any EQUATE product or sample product for use:
- (A) In any commercial or development application that is intended for contact with human internal body fluids or body tissues, regardless of the length of time involved.
 - (B) In any cardiac prosthetic device application regardless of the length of time involved, including without elimination, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, ventricular bypass assisted devices;
 - (C) As a critical component in any medical device that support or sustains human life; and
 - (D) Specifically by pregnant women or in any application designed to promote or interfere with human reproduction.
- VI. EQUATE assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.