

# SÉEETEC M1600

PP Block copolymer

## Applications

- Washing Machine Parts, Cleaner Parts, Toys

## Description

- SÉEETEC M1600 is a polypropylene block copolymer for injection molding applications. It exhibits a good balance of stiffness and impact strength. It meets the FDA requirement in the code of Federal Regulations in 21 CFR 177.1520 for food contact.

## Typical properties

Characteristics	Test Method	Unit	Value
<b>Physical<sup>(1)</sup></b>			
Density	ASTM D1505	g/cm <sup>3</sup>	0.9
MFR(230℃, 2.16Kg)	ASTM D1238	g/10min	25
<b>Mechanical<sup>(2)</sup></b>			
Tensile Strength at Yield	ASTM D638 <sup>(3)</sup>	Mpa	25
Elongation at Break	ASTM D638 <sup>(3)</sup>	%	300
Flexural Modulus	ASTM D790 <sup>(4)</sup>	Mpa	1200
Izod Impact Strength (Notched, 23℃)	ASTM D256	J/m	98
Izod Impact Strength (Notched, -20℃)			39
Hardness(R-scale)	ASTM D785	-	90
<b>Thermal</b>			
Vicat Softening point (1kgf)	ASTM D1525	℃	150
Heat Deflection Temperature (4.6kgf/cm <sup>2</sup> )	ASTM D648	℃	105

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

(3) Speed of 50 mm/min.

(4) Speed of 28 mm/min.

The actual processing conditions of our products may vary and are beyond our control, establishing satisfactory performance of the resin for the intended application is the customer's responsibility.

For additional sales, order and technical assistance

Revised : 08/07/2014

Head office PO Division, LG Chem Ltd.  
Yeouido P.O.Box 672, 21<sup>st</sup> floor LG Twin Tower,  
Yeouido-daero 128, Yeongdeungpo-gu Seoul, Korea.  
Tel. 82-2-3773-7804

TS&D TECH Center . Polyolefin  
175, Gajeong-ro, Yuseong-gu, Daejeon, 305-343, Korea.  
Tel. 82-42-860-8538, 8394