



PROPERTY	VALUE	ASTM
Melt Index 190°C/ 2.16kg (g/10 min)	1.0	D 1238
Density (g/cm³)	0.919	D 1505
Dart Drop Impact, F50 (grams)	145	D 1709A
Tensile Strength at Yield (psi) MI		D 882
Tensile Strength at Break (psi) M		D 882
1% Secant Modulus (psi) M	D 29000 D 31000	D 638

Additives: No Slip, No Antiblock

LL4F 801 can - in principle - be used in food contact applications in the USA (FDA) and in Canada (HBP). Migration or use limitations may apply.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.

